



BLUESTONE INC.

P.O. BOX 304

NEW BOSTON, NEW HAMPSHIRE 03070

(800) 639-4016 – Same phone # since 1984

bsprs.

SUPERFLEX ELASTOMERIC SEALANT - FIBERED

SPECIFICATIONS

PHYSICAL PROPERTIES

Dry Adhesion (lbf/failure mode)

Aluminum	24.42/100c
Brick	25.4/100c
Concrete	24.63/100c
Galvanized steel	20.11/100c
Wood	26.30/100c
Steel	20.56/100c
Vinyl	26.44/100c

Tensile Strength at peak	855 psi
Elongation at break	725.00%
Type "A" Hardness	55
Tack free	4 hrs.
Time to cure	5 days
Product test date	08/01/00

SUPERFLEX ELATOMERIC SEALANT will bond to any surface except EPDM and Coal Tar Pitch. These coatings meet various specifications. **SUPERFLEX ELATOMERIC SEALANT** has superior adhesion to all construction materials except EPDM and Coal Tar Pitch.